

	POLYSUL FIDE INDEX	REFLUX RATE	MOLES POLYSUL FIDE	TIME	SOLVENT	TEMPER ATURE	STRENGT H	HUE
1	Low	Low	1.8	Low	Low	Low	3.4	15.0
2	High	Low	1.8	Low	Low	Low	9.7	5.0
3	Low	High	1.8	Low	Low	Low	7.4	23.0
4	High	High	1.8	Low	Low	Low	10.6	8.0
5	Low	Low	2.4	Low	Low	Low	6.5	20.0
6	High	Low	2.4	Low	Low	Low	7.9	9.0
7	Low	High	2.4	Low	Low	Low	10.3	13.0
8	High	High	2.4	Low	Low	Low	9.5	5.0
9	Low	Low	1.8	High	Low	Low	14.3	23.0
10	High	Low	1.8	High	Low	Low	10.5	1.0
11	Low	High	1.8	High	Low	Low	7.8	11.0
12	High	High	1.8	High	Low	Low	17.2	5.0
13	Low	Low	2.4	High	Low	Low	9.4	15.0
14	High	Low	2.4	High	Low	Low	12.1	8.0
15	Low	High	2.4	High	Low	Low	9.5	15.0
16	High	High	2.4	High	Low	Low	15.8	1.0
17	Low	Low	1.8	Low	High	Low	8.3	22.0
18	High	Low	1.8	Low	High	Low	8.0	8.0
19	Low	High	1.8	Low	High	Low	7.9	16.0
20	High	High	1.8	Low	High	Low	10.7	7.0
21	Low	Low	2.4	Low	High	Low	7.2	25.0
22	High	Low	2.4	Low	High	Low	7.2	5.0
23	Low	High	2.4	Low	High	Low	7.9	17.0
24	High	High	2.4	Low	High	Low	10.2	8.0
25	Low	Low	1.8	High	High	Low	10.3	10.0
26	High	Low	1.8	High	High	Low	9.9	3.0
27	Low	High	1.8	High	High	Low	7.4	22.0
28	High	High	1.8	High	High	Low	10.5	6.0
29	Low	Low	2.4	High	High	Low	9.6	24.0
30	High	Low	2.4	High	High	Low	15.1	4.0
31	Low	High	2.4	High	High	Low	8.7	10.0
32	High	High	2.4	High	High	Low	12.1	5.0
33	Low	Low	1.8	Low	Low	High	12.6	32.0
34	High	Low	1.8	Low	Low	High	10.5	10.0
35	Low	High	1.8	Low	Low	High	11.3	28.0
36	High	High	1.8	Low	Low	High	10.6	18.0
37	Low	Low	2.4	Low	Low	High	8.1	22.0
38	High	Low	2.4	Low	Low	High	12.5	31.0
39	Low	High	2.4	Low	Low	High	11.1	17.0
40	High	High	2.4	Low	Low	High	12.9	16.0
41	Low	Low	1.8	High	Low	High	14.6	38.0
42	High	Low	1.8	High	Low	High	12.7	12.0
43	Low	High	1.8	High	Low	High	10.8	34.0
44	High	High	1.8	High	Low	High	17.1	19.0
45	Low	Low	2.4	High	Low	High	13.6	12.0
46	High	Low	2.4	High	Low	High	14.6	14.0
47	Low	High	2.4	High	Low	High	13.3	25.0

48	High	High	2.4	High	Low	High	14.4	16.0
49	Low	Low	1.8	Low	High	High	11.0	31.0
50	High	Low	1.8	Low	High	High	12.5	14.0
51	Low	High	1.8	Low	High	High	8.9	23.0
52	High	High	1.8	Low	High	High	13.1	23.0
53	Low	Low	2.4	Low	High	High	7.6	28.0
54	High	Low	2.4	Low	High	High	8.6	20.0
55	Low	High	2.4	Low	High	High	11.8	18.0
56	High	High	2.4	Low	High	High	12.4	11.0
57	Low	Low	1.8	High	High	High	13.4	39.0
58	High	Low	1.8	High	High	High	14.6	30.0
59	Low	High	1.8	High	High	High	14.9	31.0
60	High	High	1.8	High	High	High	11.8	6.0
61	Low	Low	2.4	High	High	High	15.6	33.0
62	High	Low	2.4	High	High	High	12.8	23.0
63	Low	High	2.4	High	High	High	13.5	31.0
64	High	High	2.4	High	High	High	15.8	11.0

BRIGHTN
ESS

36.0

35.0

37.0

34.0

30.0

32.0

28.0

38.0

40.0

32.0

32.0

28.0

34.0

26.0

30.0

28.0

40.0

30.0

35.0

35.0

32.0

35.0

36.0

32.0

20.0

35.0

35.0

28.0

27.0

36.0

36.0

35.0

32.0

34.0

30.0

24.0

30.0

20.0

32.0

25.0

20.0

20.0

22.0

35.0

26.0

15.0

19.0

24.0
22.0
23.0
22.0
18.0
20.0
20.0
20.0
36.0
20.0
11.0
20.0
35.0
16.0
32.0
20.0
20.0