



Zdroje

Planetární průmyslové zdroje a pestrost materiálů

Geo-materiály a jejich geo-zdroje



Zdroje

- ▶ definice, pojem
- ▶ kategorie zdrojů
- ▶ struktura zdrojů v prvních etapách vývoje civilizace
- ▶ počátky uvědomělého využívání zdrojů
- ▶ význam geo-zdrojů napříč časem




Zdroje - definice

Častá definice je ve smyslu průmyslový zdroj,... zdroje obnovitelné/neobnovitelné, zdroje pro energetický průmysl, stavebnictví, strojírenství, elektrotechniku,....,



..., významným lidsko-sociálním zdrojem rozvoje lidských společenství byly asi babičky (grandparent hypothesis/theory)...



Zdroje - upřesnění

Pokud hledáme definici můžeme najít i tuto:

Zdroj je něco, co lze použít k vytváření zisků nebo výhod. Zdroje jsou často přírodními zdroji bohatství nebo faktory, okolnosti, rysy ke zlepšení kvality života.

V podnikání se zdroje přeměňují na použitelné produkty nebo služby. Zdroje země, jako je nerostné bohatství, infrastruktura, pracovní síla a ozbrojené síly, jsou využívány pro blaho lidí a také pro ekonomický a politický rozvoj. Koncept zdrojů byl aplikován v různých formách, jako je ekonomika, obchod, životní prostředí a lidská společnost.

<https://www.safeopedia.com/definition/2945/resource>

Zdroje mají tři společné rysy:

- **Užitečnost**: Zdroje se používají k uspokojení spotřebitele.
- **Omezená dostupnost**: Zdroje jsou vzhledem k poptávce nedostatečně dostupné.
- **Potenciál vyčerpání**: Zdroje se postupně snižují, jak jsou využívány.

Zdroje – kategorie, geo-zdroje

Zdroje jsou kategorizovány mnoha způsoby v závislosti na původu, jako jsou biotické nebo abiotické, obnovitelné nebo neobnovitelné a potenciální nebo skutečné zdroje.


Resource	Components	The Most Valuable Elements
1 Near Space	Celestial bodies (the Sun, planets, meteorites, comets etc.), their orbits and energies (gravitational fields, solar radiation, radiation, electromagnetic radiation)	Sunlight and thermal energy
2 Earth's Atmosphere	Troposphere, tropopause, stratosphere, stratopause, mesosphere, mesopause, Karman Line, thermosphere, thermopause, and exosphere	Oxygen and ozone
3 Solid and liquid substances in the Earth's crust	Continents and islands, soils, geo-thermal energy, the world ocean, internal bodies of water, and hydrothermal energy	Fertile soils and fresh water
4 Climate as a combination of the Earth's climate zones	Air temperature, water temperature, humidity, atmospheric pressure, light conditions	Climates suitable for the existence and reproduction of complex forms of protein life
5 Earth's Crust	Continental crust, ocean crust, mineral resources, upper mantle, lower mantle, outer core, core	Non-renewable exhaustible mineral resources
6 Biosphere as an Integral System	biota, including humans and anthropogenic systems	humans (due to their ability to shape the environment and bear responsibility for it)
7 Noosphere	information, civilization-historical experience, languages and beliefs, cultures, scientific knowledge, aesthetic and moral values, intellectual potential of humanity - collective intelligence	Intellectual potential of humanity

Počátky lidské evoluce

- miocén? - pliocén
- ochlazování mizí lesy, začínají savany – vzpřímení hominidé
- *Australopithecus afarensis* (4-3 mil. let př. n. l.) - samice Lucy
- Před 200.000 let moderní člověk (anatomicky), Afrika, migrace jinam – proč?, zdroje?, klima?....




v Keni byly objeveny kamenné sady nástrojů z doby zhruba před 2,9 milionu let (Paranthropus)



Krise lidského druhu

- ▶ 70.000 let, supervulkán, Sumatra – jezero Toba (cca 100km), ochlazení, trvání cca 1000let
- ▶ 3000-10000 lidí na planetě (asi poslední období, kdy zdroje byly dostatečné😊)




silicity, obsidiány



Období lidských dějin a jejich zdroje

- ▶ doba kamenná (2,5mil – 10-8-5tis.): Paleolit, mezolit (období pleistocénu),
neolit (zemědělství, keramika, industrie, oděvy, domy), eneolit,
- ▶ doba bronzová
- ▶ doba železná
- ▶ ...
- ▶ ...
- ▶ doba „plastová“ - antropocén

prehistorická těžba
pazourku



Kámen/horniny – primární zdroje

Výchozy na povrchu, organizované lomy, ale uměli i hloubit jámy



Deserves a place on the World Heritage List: The Gebel el-Silsila ancient sandstone quarries. Photo: Tom Heldal




Craig Rhos-y-felin, Wales, ryolit na Stonehenge

"We have dates of around 3400 BC for Craig Rhos-y-felin and 3200 BC for Carn Goedog, which is intriguing because the bluestones didn't get put up at Stonehenge until around 2900 BC" said Professor Parker Pearson.



Si Khio Ancient Quarry is in the Phu Phan Formation, which was laid down about 120 million years ago. The sandstone here is grey and rather coarse but lacks conglomerate, making it good for carving. Thailand.




dnešní stav těžebních jam a mramorový náramek, Bílý Kámen u Sázavy

Minerály - krystaly

proč právě křišťál?, připomíná led...,
viděli dovnitř, chtěli použít neobvyklý
materiál připomínající led?

Křemenná žíla v granitu



křemen-křišťál, nástroje, Pleistocene,
Uruquay

materiály pro nástroje i duchovní život?....

Optické krystaly




Syntetické diamanty



naleziště křišťálů
v Alpách



Nd YAG Nd Doped Yttrium Aluminium
Garnet Laser Crystal– MSE Supplies
LLC




Neolit – přelomové období využívání zdrojů (neolit až bronz)


Na Blízkém východě jsou to hlavně obydlí a města, stavěná z hlíny a nepálených cihel

Mezi nejstarší sídliště patří Göbekli Tepe
Göbekli Tepe a Nevalı Çori z 10.–9. tisíciletí ve východním Turecku


Brittany: Lann-Mané-Bras dolmen: a view of the central group



v Evropě se zachovaly hlavně megality



Göbekli Tepe



The 12,000-year-old site of Göbekli Tepe, in southeastern Turkey

Göbekli Tepe is a Neolithic archaeological site in the Southeastern Anatolia Region of Turkey. Dated to the Pre-Pottery Neolithic, between c. **9500 and 8000 BCE**, the site comprises a number of large circular structures supported by massive stone pillars. The 15 m (50 ft)-high, 8 ha (20-acre) tell also includes many smaller rectangular buildings, quarries, and stone-cut cisterns from the Neolithic. The oldest permanent human settlements anywhere in the world.



Aerial view of the main excavation area, showing circular enclosures A, B, C and D and a number of rectangular structures.


Nevalı Çori

Nevalı Çori (Turkish: Nevalı Çori, Kurdish: Newala Çorî) was an early Neolithic settlement on the middle Euphrates, in Şanlıurfa Province, Southeastern Anatolia, Turkey. The site is known for having some of the world's oldest known temples and monumental sculpture. Together with the earlier site of Göbekli Tepe, it has revolutionised scientific understanding of the Eurasian Neolithic period.


Nevalı Çori, south-eastern Turkey, head with snake; limestone. Şanlıurfa Müzesi. Early to Middle PPNB. Photo courtesy of Euphrat-Archiv, Berlin-Heidelberg.



The local **limestone** was carved into numerous statues and smaller sculptures, including a more than life-sized bare human head, a statue of a bird. The free-standing anthropomorphic figures of limestone excavated at Nevalı Çori belong to the earliest known life-size sculptures. Comparable material has been found at Göbekli Tepe.



Humanoid T-shaped pillars from Nevalı Çori (left) and Göbekli Tepe (right)




"Temple" at Nevalı Çori

Fragment of Neolithic art from Nevalı Çori depicting a hunting scene




Neolit – 10000-5000 BC



Some of the European flint (pazourek), chert and obsidian sources used during the Neolithic period and the approximate areas of distribution of artefacts from the sources.



Pazourky v křídových sedimentech – baltické pobřeží



Map of the spread of Neolithic farming cultures in Europe, dates in year BCE

Šíření zemědělství z Mezopotámie do stř. Evropy



Pre-Pottery Neolithic B

Around 8000 BCE, before the invention of pottery, several early settlements became experts in crafting beautiful and highly sophisticated containers from stone, using materials such as alabaster or granite, and employing sand to shape and polish. Artisans used the veins in the material to maximum visual effect. Such objects have been found in abundance on the upper Euphrates river, in what is today eastern Syria, especially at the site of Bouqras. These form the early stages of the development of the Art of Mesopotamia.



Footed bowl in **granite**, Syria,
end of 8th
millennium BC.



Green **aragonite**
tripod vase Mid-
Euphrates 6000 BC
Louvre Museum
AO 28386




Alabaster pot,
Mid-Euphrates
region, 6500 BC,
Louvre Museum

During this period, one of the main features of houses is a thick layer of white clay plaster flooring, highly polished and made of lime produced from limestone. It is believed that the use of clay plaster for floor and wall coverings during PPNB led to the discovery of pottery.

Pre-Pottery Neolithic B (PPNB) is part of the Pre-Pottery Neolithic, a Neolithic culture centered in upper Mesopotamia and the Levant, dating to c. 10,800 – c. 8,500 years ago, that is, 8800–6500 BC.



Çatal Hüyük, Turkey



Çatal Hüyük, ancient settlement in Anatolia, Turkey, from c. 6500 BC



Terracotta mother goddess statue, from Çatal Hüyük or Çatalhöyük, 6th millennium BC

Bronze age




Initially the ore would be recovered only from the **surface**. However later Bronze age man started to recover the ore from shallow open pits called bell pits. At Mynydd Parys the base of some of these bell pits have been discovered up to 50 feet **underground**.


Cu+Sn

The Provenance, Use, and Circulation of Metals in the European Bronze Age: The State of Debate
Miljana Radivojević, Benjamin W. Roberts, Ernst Pernicka, Zofia Stos-Gale, Marcos Martinón-Torres, Thilo Rehren, Peter Bray, Dirk Brandherm, Johan Ling, Jianjun Mei, Helle Vandkilde, Kristian Kristiansen, Stephen J. Shennan & Cyprian Broodbank
Journal of Archaeological Research volume 27, pages 131–185 (2019)

An overview of Chalcolithic and Bronze Age copper mines (Δ) in Europe together with settlements, shipwreck, and hoard sites mentioned in the text (o). 1, Ross Island; 2, Mount Gabriel; 3, Parys Mountain; 4, Great Orme; 5, Cwm Ystwyth; 6, Alderley Edge; 7, Ecton; 8, Must Farm; 9, Salcombe; 10, Langdon Bay; 11, St Renan; 12, El Aramo; 13, La Profunda; 14, El Milagro; 15, San Cristóbal de Logrosán; 16, Cuchillares; 17, Chinflón; 18, La Loba; 19, Berrocal; 20, Causlat; 21, Loma de la Tejería; 22, Cabrières; 23, St. Véran; 24, Sursee-Gammainsell; 25, Libiola; 26, Monte Loreto; 27, Trentino; 28, Schwaz-Brixlegg; 29, Glemmtal; 30, St. Veit; 31, Mitterberg-Bischofshofen; 32, Nebra; 33, Tollense; 34, Pile; 35, Egtved; 36, Grotta della Monaca; 37, Eisenerz; 38, Mannesdorf; 39, Hainburg; 40, Špania Dolina; 41, Hajdúsámon; 42, Apa; 43, Jarmovac; 44, Ždrelo; 45, Majdanpek; 46, Rudna Glava; 47, Kastri; 48, Thermi; 49, Aibunar; 50, Poliochoni; 51, Troy; 52, Lavrion; 53, Uluburun; 54, Cape Gelidonya; 55, Kanesh; 56, Nahal Mishmar



(Adapted from Bray et al., p. 206, fig. 2; prepared by P. Bray and T. P. Leppard)
Distribution of arsenical copper Group 2 as defined by Bray et al. (2015) (traces: As > 0.1%, Sb, Ni, and Ag < 0.1%) in the European and western Asian Early Bronze Age. The inset map of Europe suggests an Atlantic coast transport of such metal into France and Britain and possibly another source coming into southeastern Europe via Anatolia. The larger map of western Asia is less complete but shows the distribution of this metal in the Near East with possible sources in Anatolia and Afghanistan




Great Orme Bronze Age copper mines



Uncovered in 1987 during a scheme to landscape an area of the Great Orme, the **copper** mines discovered below the ground represent one of the most astounding archaeological discoveries of recent times. Dating back **4,000 years** to the Bronze Age, they change our views about the ancient people of Britain and their civilized and structured society 2,000 years before the Roman invasion.



Zdroje kovů a metallurgie



Metallurgy in the Balkans (c. 6200–3700 BC). Rudna Glava is the earliest documented copper mine in the whole of Eurasia.




The fist-sized slag from Mušiston (a) and exposed metal prills (b) and charcoal flakes (c) from its interior (photos: D Berger)



Zdroje doby bronzové


SPREAD OF BRONZE AND LOCATION OF TIN DEPOSITS



The upper Ili Valley in northwest Xinjiang is a crucial place for the study of early interactions between the Eurasian Steppe and northern China. This paper presents scientific analytical results and examines the use and production of copper alloys in the region with regard to the transregional exchange of materials and technology.



The **Bronze Age in China** began around **2000 BCE**, and the earliest excavated ritual bronze vessels date to around 1600 BCE.



Cesty materiálů i výrobků




Miniature figure of a sun disc on a stand, **bronze and amber**, probably Jutland, Denmark. Height: 6.9 cm.
Photo: A. Mikkelsen, the National Museum of Denmark.

Varberg, Jeanette & Kaul, Flemming & Gratuze, Bernard. (2020). Bronze Age Glass and Amber Evidence of Bronze Age long distance exchange.
Available from:
https://www.researchgate.net/publication/342787189_Bronze_Age_Glass_and_Amber_Evidence_of_Bronze_Age_long_distance_exchange [accessed Dec 15 2022].

cesta suroviny od zdroje --- výroba --- cesta k užívání

Bronze Age amber routes
(after CZEBRESZUK2011)



Necklace made of **amber** beads with a central **blue glass bead**. Found at Všekary-Husté Leče (Domažlice District), tumulus 2, Middle Bronze Age. Museum of Western Bohemia in Pilsen.






Figure 2. Extensive excavations on the saltflat edge of a saline sump in Wadi el Natrun, Egypt

Sklo mladší doby bronzové



Ölby, Denmark. Both made of Egyptian cobalt-blue glass from the 14th century BC. Photo: A. Mikkelsen, National Museum of Denmark.

- ▶ Man-made glass only becomes common in Syria-Mesopotamia and Egypt in the Late Bronze Age (LBA), after the fifteenth century BCE glass revolution (Peltenburg, 1987).
- ▶ 1400-1300 BC
- ▶ sklo (valouny křemene, křemenec (silicifikovaná sedimentární hornina), natron – soda, popel, Sb, Pb, Cu)
- ▶ Zdroj některých barvících kovů na Kavkazu (podle izotopů Sb, Degryse et al. 2015)
- ▶ hlavní zdroje už nutně měly nějaké těžební zvyklosti a obchodní vztahy

Natron, soda - NaHCO_3
Wadi El Natrun, Egypt

Between Egypt, Mesopotamia and Scandinavia: Late Bronze Age glass beads found in Denmark.
Journal of Archaeological Science, Volume 54, February 2015, Pages 168-181

Glassmaking in Bronze-Age Egypt

Little is known about the production of glass in the ancient world. One early source, Pliny the Elder (AD 23 – 89), reported the tale of **natron (soda)** merchants who, when they stopped to prepare a meal, supported their cooking vessels on the beach with blocks from their cargo. The heat of the fire fused natron and sand, and a new substance was formed. This, Pliny says, was the origin of glass.


Glass-like materials were used in Egypt long before the production of glass itself. Egyptian **faiience**, a popular material used in the production of amulets and small vessels, was a mixture of quartz sand with an alkali binder. It was molded, and then fired, causing a bright glaze to migrate to the surface. Real glass is more difficult to produce, because its ingredients must be heated to a high enough temperature to melt and then fuse completely.....



Trade in glass. This map shows the location of sites discussed in the text in the context of glass production and trade around the Mediterranean in the Late Bronze Age. Evidence presented by Rehren and Pusch strengthens the case for primary glass production in Egypt.CREDIT: PRESTON HUEY/SCIENCE


<https://www.science.org/doi/10.1126/science.1112553>

Glassmaking and movement in the Late Bronze Age



SOURCE: C.M. JACKSON / SCIENCE 2005 WITH MODIFICATIONS BY TH. REHREN

KNOWABLE MAGAZINE



Struktura zdrojů pro zajištění základních potřeb

potrava
(biozdroje) a
zajištění potravy
(bio/geozdroje)

energie
(bio/geo)

nástroje
(bio/geo)

obydlí
(bio/geo)

obrana
(bio/geo)

kultura
(bio/geo)

Potrava a zajištění potravy



Fosforit,
sedimentární
hornina obsahující
apatit, Maroko
(50% světových
zásob)

alamy

Image ID: D3EXHF
www.alamy.com




Apatit, $\text{Ca}_5[(\text{F}, \text{Cl}, \text{OH}) | (\text{PO}_4)_3]$



Sylvín, KCl

...a další K a Mg soli, = chemické sedimenty – evaportity, odpařování mořské vody

Amoniak a výroba hnojiv,
Haber-Bosch proces,
zdrojem dusíku je vzduch



zásoby draselných a hořečnatých solí:
Kanada 50% světových zásob,
Německo 17%



Energie



Energetické zdroje





- ▶ Dřevo – významná surovina k výrobě energie až do začátku 20.století
- ▶ První stroje – pára – uhlí
- ▶ Ropa: deriváty – petrolej – oleje – benzín
- ▶ Elektřina – turbíny vodní – parní – plynové
- ▶ Uhelné elektrárny – uhlí
- ▶ Jaderné elektrárny – obohacený uran (gaseous diffusion, gas centrifuging)

- ▶ Ložiska uhlí
- ▶ Ložiska ropy a plynu, nekonvenční ložiska - hydráty metanu
- ▶ Ložiska uranu
- ▶ Nové typy zdrojů obnovitelné energie (solární, větrné)
- ▶ ...Zdroje geotermální energie
- ▶ budoucí: termojaderná fúze (izotopy vodíku),....



Zdroje pro energie - příklady

Usibelli Coal Mine, AK



Nástroje a předměty



Set of 1,500-year-old farming tools discovered in Turkey



Fe - dřívější materiálová „střídmost“ a jednoduchost

Dnešní nástroje, jejichž materiálem jsou hlavně ocel a slitiny, ale i....



dnešní materiálová komplexnost:
kovy, slitiny, plast, pryže-kaučuk

ELEMENTS OF A SMARTPHONE

ELEMENTS COLOUR KEY: ● ALKALI METAL ● ALKALINE EARTH METAL ● TRANSITION METAL ● GROUP 13 ● GROUP 14 ● GROUP 15 ● GROUP 16 ● HALOGEN ● LANTHANIDE


SCREEN



Indium tin oxide is a mixture of indium oxide and tin oxide, used in a transparent film in the screen that conducts electricity. This allows the screen to function as a touch screen.

The glass used on the majority of smartphones is an aluminosilicate glass, composed of a mix of alumina (Al_2O_3) and silica (SiO_2). This glass also contains potassium ions, which help to strengthen it.

A variety of Rare Earth Element compounds are used in small quantities to produce the colours in the smartphone's screen. Some compounds are also used to reduce UV light penetration into the phone.



ELECTRONICS



Copper is used for wiring in the phone, whilst copper, gold and silver are the major metals from which microelectrical components are fashioned. Tantalum is the major component of micro-capacitors.

Nickel is used in the microphone as well as for other electrical connections. Alloys including the elements praseodymium, gadolinium and neodymium are used in the magnets in the speaker and microphone. Neodymium, terbium and dysprosium are used in the vibration unit.

Pure silicon is used to manufacture the chip in the phone. It is oxidised to produce non-conducting regions, then other elements are added in order to allow the chip to conduct electricity.

Tin & lead are used to solder electronics in the phone. Newer lead-free solders use a mix of tin, copper and silver.

BATTERY



The majority of phones use lithium ion batteries, which are composed of lithium cobalt oxide as a positive electrode and graphite (carbon) as the negative electrode. Some batteries use other metals, such as manganese, in place of cobalt. The battery's casing is made of aluminum.

Magnesium compounds are alloyed to make some phone cases, whilst many are made of plastics. Plastics will also include flame retardant compounds, some of which contain bromine, whilst nickel can be included to reduce electromagnetic interference.

CASING



Obydlí

'house inside a rock,' Amey Kandalgaonkar



Ancient rock houses intermingled with modern houses in Cappadocia, využití měkkých hornin



část města - středověk



Meteora has a view of the town below.
Shutterstock, Meteora monasteries in Greece
(využití tvrdých hornin)

The Katshki Pillar Monastery, Chiatura, Georgia,
The River House on Drina river, near the town of
Bajina Basta, Serbia,
Casa do Penedo or 'house of stone', in northern
Portugal's Fafe mountains,
The only house on Elidaey island in Iceland



keltská polozemnice



sulfidy Pb-Ag-Zn-Cu




Obrana první demokracie

A mining shaft located in Thorikos which is home to several mining spots in the greater Laurion mining region



Map of Southern Attica, showing the locations of the mines at Laurion. (Dictionnaire des antiquités grecques et romaines, tome 3, volume 2, Hachette, 1877-1914, p. 1850)

Moderní rekonstrukce athénské trirémy (o kloun – slitina s mědí).



5.-6.st BC Atheny, v době druhé perské invaze do Athén měli 3000 t stříbra – zdroj k financování stavby lodí (trirémy), bitva u Salamis 480 BC

Poté, co Peršané kolem roku 479 př. n. l. uprchli z Athén, bylo potřeba město přestavět – olovo – potrubí, mramor – stavby (Pantheon-Acropolis,...., sochy, opevnění.



Pentelic marble quarry

Obrana – předměty a materiály

Zbraně Vikingů




Během mezolitu (10 000-7000 BC) došlo k technologické revoluci ve vývoji zbraní, která měla stejný význam jako pozdější největší objevy moderní doby (vynález **střelného prachu** apod.) - vynález **luků a šípů**.

Střelný prach – významná pomoc při těžbě surovin a stavbách, ... a ve válečných konfliktech, vynalezen v Číně (7.-9.stol.), v Evropě ve 13.stol., (Typické složení černého střelného prachu je: **75 % KNO₃ – ledek, dusičnan draselný, 10 % síry** a 15 % dřevěného uhlí (uhlík - C))

V roce 1887 si Alfred Nobel nechal patentovat bezdýmý střelný prach pod názvem ballistit a jeho dalším zdokonalením vznikl dnes nejpoužívanější kordit. Hlavní složkou je střelná bavlna kombinovaná s nitroglycerinem a jinými nitroglykoly.

yì wo feng (China)



zdroje:
Fe... W ...

The Power Of Javelin Missile



Spousta oceli a digitálních přístrojů

USS Gerald Ford, the **nuclear**-powered carrier USS Gerald R. Ford (CVN 78). The Ford itself will cost US taxpayers \$12.8 billion in materials and labor. This doesn't take into account the \$4.7 billion spent in research and development of the new carrier class. And, seriously, we're talking about a lot of labor ... An aircraft carrier weighs over 100,000 tons, ... 60,000 tons of **steel** ...



Kultura a její materiálové potřeby

Kultura – ve smyslu tvůrčí aktivity, v užším smyslu slova, kulturou se rozumí jen ta část specificky lidských činností, která je tvůrčí a neslouží bezprostředně k uhájení života.

Kultura (lat. cultura, „to, co je třeba pěstovat“) je označení pro veškeré jednání člověka, které je vnímáno v kontrastu s přírodou (dvojice "Kultura a příroda"). V užším slova smyslu jde o soubor vybraných a tvůrčích lidských činností, jako je například literatura, umění, divadlo, náboženství, případně i vzdělávání.)



The crystal skull at the British Museum, similar in dimensions to the more detailed Mitchell-Hedges skull. Dokládá snadné šíření legend?



Originálním optickým klamem pak upoutává pozornost socha Dotyky a distance od Aleše Veselého. Kampus MU, Brno-Bohunice.

Monstrance

1. polovina 15. století (před 1438 ?)

zlacené stříbro; výška 91 cm, šířka koruny 32 cm, průměr nohy 23–26.8 cm,
Římskokatolická farnost sv. Michala v Olomouci
zapůjčeno do stálé expozice Arcidiecézního muzea Olomouc




Běžné i vzácné materiály




A handprint found in Indonesia and believed to be at least **39,900** years old. Photo: Kinez Riza via Nature, discovered on the island of Sulawesi in Indonesia


Velmi běžné reakce v přírodě:



Pyrit ----- limonit



Kalahari desert, South Africa, také těžba hlinky, 40.tis.let – viz na jiném místě



Himba woman (Namibia) wearing the protective otjize paste (red ochre mixed with butterfat) over her hair /
Photograph by Sean Tucker



malířství – složení barev, přírodní dnes i syntetické



Lapis lazuli



The Starry Night
Vincent Van Gogh (1889)



Girl With a Pearl Earring
Johannes Vermeer (1665)



The Virgin in Prayer
1640-1650



Bacchus and Ariadne
Titian (1520-1523)

3D umění


Mount Rushmore in South Dakota



Wilendorfská venuše – příklad využití vhodného kamenného a neobyčejného materiálu (jurský oolitický vápenec), 22-20tis. let, 1908 - Aggsbach u Melku, u Dunaje




Marble Quarries
in Carrara, Italy



David, Michelangelo 1475-1564

Moderní sochařství
– kámen, kov



Uluru - spiritual connection with the continent

Located in the heart of the continent, Uluru is one of Australia's most recognisable landmarks – a red sandstone monolith that rises 348 metres above the desert. It is a natural wonder, a symbol of Aboriginal land rights and a source of spiritual connection with the continent.

For many, Uluru and its neighbour Kata Tjuta aren't just rocks, they are living, breathing, cultural landscapes that are incredibly sacred. Known as being the resting place for the past ancient spirits of the region. A large portion of its surrounds is Indigenous Protected Area, which protects the biodiversity, cultural, and social features within. Cultural customs and traditions are handed down and link the people with the land and animals.



Hornina (arkose sandstone – arkozový pískovec, arkóza) a z něho přirodní útvar byl(je) uctívánou duchovní entitou, UNESCO, Uluru (Ayers Rock-Mount Olga) Biosphere Reserve, Australia

Shrnutí - zdroje

- ▶ Shrnutí o využívání geozdrojů:
- ▶ Z litosféry, z hydrosféry, z atmosféry
- ▶ Kámen, minerály, prvky, kovy, plyny, kapaliny
- ▶ Zdroje surovin pro 1) zajištění potravy, 2) zajištění energie, 3) předměty - potřebné nástroje, 4) obydlí, 5) přežití – obrana, 6) kulturu
- ▶ Prakticky žádný materiál-surovinu a typ zdroje/ložiska od pravopocátků až dodnes jsme neopustili: dřevo (jen omezili), kámen, minerály, kovy, uhlovodíky, atmosféra – získáváme plyny, ...
- ▶ ...některé začínáme opouštět: uhlí jako energetickou surovinu, uvažuje se o uranu, resp. jaderné energetice, ...ale ještě je asi brzy, svět zdrojů se mění...

