



Mesoporous Materials

Amorphous, disordered - silica xerogels

Ordered, amorphous walls


Pore diameter, d [nm]	Material	Example
$d > 50$	Macroporous	Aerogels
$2 < d < 50$	Mesoporous	Xerogels
$d < 2$	Microporous	Zeolites

Pore size distribution




Mesostructure Assembly


A



B



C



Mesoporous Materials

MMS mesoporous molecular sieves

MCM-n Mobil Composition of Matter

M41S


Discovered 1992

A - lamellar MCM-50


B - hexagonal MCM-41

C - cubic MCM-48


Inverse hexagonal



A



B




C

Mesoporous Materials

**X-ray
Diffraction
Pattern**



**MCM-41
(Hexagonal)**




**Possible
Structures**




**MCM-48
(Cubic)**



**MCM-50
(Stabilized Lamellar)**



**Silica
Sheets**



Supramolecular Templating

Surfactants - amphiphilic molecules, polar (head group) and nonpolar (chain, tail) part
lyophilic, lyophobic


Ionic surfactants, cationic, anionic, zwitterionic

Nonionic amines, polyethyleneoxides

A - normal surfactant molecule

B - gemini

C - swallow tail



Surfactants


Hydrotrope
(flexible surfactant)



Bolaform surfactant




Diblock copolymer
surfactant




Classical surfactant
(rigid surfactant)



Gemini surfactant
(dimeric)



Polymeric surfactant



Surfactants

Anionic

- *sulfates*: $C_nH_{2n+1}OSO_3^-Na^+$
- *sulfonates*: $C_nH_{2n+1}SO_3H$
- *phosphates*: $C_nH_{2n+1}OPO_3H_2$
- *carboxylates*: $C_nH_{2n+1}COOH$


Cationic

- *alkylammonium salts*: $C_nH_{2n+1}(CH_3)_3NX$ X = OH, Cl, Br, HSO₄
- *dialkylammonium salts*: $(C_{16}H_{33})_2(CH_3)_2N^+Br^-$

Noionic

- *primary amines*: $C_nH_{2n+1}NH_2$
- *polyethyleneoxides*: $HO(CH_2CH_2O)_nH$


Supramolecular templating



Phase diagram of $C_{16}TMABr$


CMC = critical micelle conc.

Micelles - Supramolecular Templates



Micellar shapes


A -spherical, B - rod-like, C - lamellar




Micelles in media

A - normal, in polar solvent, H₂O

B - inverse, in nonpolar solvent, organics



Micellar shapes



Micellar structures

A) sphere, B) cylinder, C) planar bilayer,
D) reverse micelles, E) bicontinuous phase, F) liposomes).


Critical packing parameter – CPP

$$\text{CPP} = V_H / a_0 l_c$$

V_H volume of the hydrophobic part, a_0 surface area of the hydrophilic part, l_c critical chain length:

$$l_c \leq 1.5 + 1.265 n \quad [\text{\AA}]$$

n number of carbon atoms. l_c depends on the chain shape.



CPP

surfactant

micelle shape

< 0.33

linear chain, large head

spherical

0.33 - 0.5

linear chain, small head


cylindrical

0.5 - 1.0

two chains, large head

bilayers


Surfactant Molecules




Conical (*icecream cone*, A)

Inverse conical (*champagne cork*, B)

Surfactant Molecules






L_1 = micellar solution; N_c = nematic phase; H_1 = normal hexagonal phase (MCM-41; SBA-15);
 V_1 = normal bicontinuous cubic phase (MCM-48); L_α = lamellar phase (MCM-50)


path A, the micellar solution route
 path B, the lamellar phase route
 path C, the nematic phase route

Mechanism of the mesoporous material formation (hexagonal, MCM-41)


LCT Liquid Crystal Templating





General Liquid Crystal Templating (LCT) Mechanism





SLC Silicatropic Liquid Crystals









Ion Exchange / Cooperative Nucleation




SLC Assembly



Lamellar to Hexagonal Transformation



Silicate Rod Assembly




- **Electrostatic interactions**

a) **S⁺I⁻**

I = silicate

S = trimethylammonium




b) **ST⁺**

I = Fe²⁺, Fe³⁺, Co²⁺, Ni²⁺,

Mg²⁺, Mn²⁺, Pb²⁺, Al³⁺

S = sulfonane



c) **S⁺XI⁺**

I = silicate – polyelectrolyte
positive charge

X = Cl

S = trimethylammonium



d) **S⁻M⁺I⁻**

I = aluminate

M = Na

S = phosphate




- **Hydrogen Bond**

a) **S⁰I⁰**

I = silicate


S = ammine



b) **N⁰I⁰**

I = silicate

N = polyethylenoxide










- **Covalent Bond**



a) **S-I**

I = niobate, tantalate

S = ammine









MCM-41


20Å




60Å



40Å






100Å




Prepared with Mesitylene Addition


TEM micrograph of hexagonal molecular sieve




TEM image of the Pd-grafted mesoporous silicate material




Silicate Layer Puckering




Charge Density Matching




Folding Sheets





XRD of hexagonal MCM-41



XRD of lamellar MCM-50









$$a_0 = \frac{2d_{100}}{\sqrt{3}}$$

Gas Adsorption Isotherms

Pore filling



Template Removal



Mesoporous Platinum Metal

$\text{H}_2[\text{PtCl}_6]$ or $(\text{NH}_4)_2[\text{PtCl}_6]$


$\text{C}_{16}(\text{EO})_8$

Assembly of liquid crystalline phase


Reductants: Fe, Zn, Hg, NH_2NH_2

Washed with acetone, water, HCl


SEM (upper) and TEM (lower) images of mesoporous Pt metal show particles 90-500 nm in diameter and a pore diameter of 30 Å and a pore wall thickness of 30 Å.




Surface Silanols in MCM-41 Pores




Chemistry inside the Pores






bis(benzene)chromium



toluene




potassium fulleride



sodium



nickelocene



cobaltocene