

Prosthetics II.

Fixed dentures

Inlay, root canal inlay

Fixed dentures


- Cemented (fixed) on/in pilots, abutment teeth.
- Inlays (inlays, onlays, overlays, partial crowns).
- Crowns
- Bridges

Inlays

Composit, ceramic

Metal





Fixed dentures

- Cemented on the teeth – crowns, bridges, inlays



Fixed bridge

Fixed dentures

- Material – metal alloy, ceramics



Removable dentures

- Partial
- Complete (full)



Procedures

- In dental surgery
- In dental laboratory
- Special instruments
- Basic (main) materials
(metal alloys, ceramics, polymers)
- Auxilliary (accessory) materials
*(impression, carving, die, insulating
investing, grinding, polishing)*

Manufacturing of dentures

Model of gypsum (plaster) – model of a denture (wax pattern).

Model of a denture (wax pattern) directly in the mouth – rarely.

Denture is formed without a wax pattern in the dental lab.

Manufacturing of dentures

Model of gypsum (plaster) – model of a denture (wax pattern).

Impressions of the jaw - negativ

The impression is filled with a casting material (gypsum) – poured into



Model
(various purpose)

Models

- Working model – the denture is produced on this model (special procedures)
- Opposing model (antagonal) - necessary for the recognition of intermaxillary relationship
- Bite registration - wax

Manufacturing of dentures

- The denture (not the denture itself but the model of the denture) is produced on the working model.
- The model of the denture is made of the carving wax.
- The wax is replaced by the main (base) material.


Fabrication of dentures


The model (wax) of the denture is invested


The wax is removed from the form and the base material is placed into the form.

Wax removal:


*The wax is burned out (for metal alloys)
or removed by hot water (for polymers)*








Plaster





The model (wax pattern)




The investing material

The model
(wax pattern)







Manufacturing of dentures

The method described above = indirect method



Manufacturing of dentures

Direct method

Manufacturing of dentures

Direct method

No impression

The model of the denture is made directly in
the mouth

For inlays only

Inlays

- Rigid fillings
- Manufactured in a dental lab
- Direct or indirect method
 - Direct method rarely
 - Indirect method most common

Inlay

■ Crown inlay

- a part of a clinical crown is replaced

■ Root canal inlay

- The inlay is cemented into the root canal and replaces a crown (abutment tooth – stump, snag)

Crown inlay

Material

- *Composit*
- *Ceramics*
- *Metal Alloys*



Angle of convergence

- 0° - maximum
- 6° - very good
- 15° - acceptable
- 20° - insufficient

Optimum 6° - 15°.

Crown inlays

Indikations



- A big lost of dental tissues
- Big interdental spaces
- Next to the crowns and bridges made of metal alloy

Crown inlays


Contra - indication

1. *Too small - shallow (flat) cavities*
2. *High caries risk*
3. *Frontal area (metallic)*



Inlay





Onlay





Overlay



Partial crown



Crown




Retention of rigid fillings


Whitstand capability against axial forces:

Geometry of the preparation


(facilitating shape)

Quality of the luting material





Angle of the convergence



Retaining areal

- Surface of contact

Rigid filling

Inlay or crown (internal, outer, combined)



Stability of rigid fillings

Whitstand capability against horizontal forces

Angle of convergence


Axial length contact surface





Basic rules of cavity preparation

- Box
- No undercuts
- Light divergence of the walls (facilitating shape)



Box

Undercuts

Simple box

Facilitating form


Inlay of metal alloy

■ Direct method


■ Indirect method

Inlay of metal alloy

➤ Direct method



Direct modellation in the mouth
Special wax – casting wax,
(special polymers)
Sprue pin
Investment
Method of the lost wax



Inlay of metal alloy

Direct method

- Central cavities (class I., classs V.)
- Root canal inlays

Inlay of metal alloy

Indirect method

Taking of the impression


Model

Modellation of the casting wax,
(special polymers)

Sprue pin



Investment


Method of the lost wax

















Dokončená preparace

Nasazená rekonstrukce





Aesthetic inlays – composite materials, ceramics




Special procedure




Indirect method always





Root canal inlay

Root canal filling



Root post

Core

Crown

Root canal inlay

Indication :

Restoration for teeth with lost crown
(cca 2/3 of the crown)

It is anchored in the root canal
(the tooth must be endodontically treated)

The coronal part is formed as a stump for
the crown

It enables to treat this teeth with crown

Contraindication


- Teeth that cannot be treated endodontically
- Decay of the root or coronal part of the crown
- Less than 1mm hard dental tissues supragingivally
- Destruction of root canal walls circulary


Root canal inlay - preparation

- Removal of the root canal filling (2/3), 4 mm of the root canal filling must be left.
- The third rule

Gates, Peeso – Largo,




Beutelrock – these burs has „flame form“





1- 2mm


Preparation



4mm at least

2/3 of the
root canal length

1/4 of the total length



Direct method

Isolation

**Modellation – casting wax,
heated, flowing**

Sprue pin with reservoir

Sprue cone

Investment

Lost wax method

(burntout in the special oven)



Indirect method

Impression

Model


**Modellation – casting wax,
heated, flowing**

Sprue pin


Investment

Lost wax method


(burntout in the special oven)



Indirect method




Impression




Wire


Impression tray

Impression material






Model



Modellation



Insulation

Indirect method

Impression

Model


**Modellation – casting wax,
heated, flowing**


Sprue pin


Investment


Method of the lost wax

(burntout in the special oven)











The investing material


The model
(wax pattern)






The investing material

The model
(wax pattern)



The investing material

The model
(wax pattern)



■ Final product



Cementation

- Zinkoxid phosphate cement
- Lentulo
- Vaseline
- Removal of access of the cement

