

# Sonochemical Reactions

**Chemical changes/reactions induced by ultrasound**

**No direct interaction of ultrasound field with molecules (in contrast to photochemistry, ...)**

- **Liquid phase reactions – chemical reactions driven by cavitation effects**
- **Solid state reactions – introduction of defects = speeding up diffusion**

# **Sound**


**Sound = pressure waves = periodic compression/expansion cycles traveling through a medium possessing elastic properties (gas, liquid, solid)**

**Liquids and gases – longitudinal pressure waves – compression/rarefaction  
Solids – longitudinal and transverse waves**


**The energy is propagated as deformations (tensile/compressive stress) in the media**

**The molecules oscillate about their original positions and are not propagated**

**The propagation of a sound wave = the transfer of vibrations from one molecule to another**



# Longitudinal Pressure Waves



# Sound

**In a typical liquid, the speed of sound decreases as the temperature increases, at all temperatures.**

**The speed of sound in water is almost five times greater than that in air ( $340 \text{ m s}^{-1}$ )**

<b>Substance</b>	<b>Speed of sound, <math>u</math> [<math>\text{m s}^{-1}</math>]</b>
------------------	--

Air	343
-----	-----

Helium	965
--------	-----

Water	1482
-------	------

Lead	1960
------	------

Steel	5960
-------	------

Granite	6000
---------	------

# Speed of Sound


The speed of sound ( $u$ )

$$u^2 = 1/\kappa_S \rho = [\partial P / \partial \rho]_S \sim 1/(\langle V \rangle^2)$$

$\kappa_S$  = adiabatic compressibility

$\rho$  = density

P = pressure



# Sound Intensity

$$\text{Sound Intensity} = \text{Power} / \text{area} = \text{Watts/m}^2$$

<i>Source of Sound</i>	<i>Intensity (W/m<sup>2</sup>)</i>	<i>Sound level (dB)</i>
Jet Airplane 30 m away	$10^2$	140
Air-raid Siren, nearby	1	120
Threshold of Pain	$10^{-1}$	120
Concert	$\sim 10^{-1}$	115
Riveter	$10^{-3}$	100
Busy Traffic	$10^{-5}$	70
Normal Conversations	$10^{-6}$	60
Whisper	$10^{-10}$	20
Threshold of Hearing	$10^{-12}$	0

0 dB ( $10^{-12}$  W/m<sup>2</sup>)

10 dB = 10 times as intense

20 dB =  $10^2$  times as intense

30 dB =  $10^3$  times as intense

120 dB =  $10^{12}$  times as intense

# Acoustic Pressure

$$P_a = P_A \sin 2\pi f t$$

$P_a$  acoustic pressure

$P_A$  pressure amplitude


$f$  sound frequency

$$c = \lambda f$$


(for 20 kHz,  $\lambda = 7.5$  cm)

$$P_{\text{total}} = P_a + P_h$$

$P_h$  hydrostatic pressure



# Acoustic Pressure



**Compression and  
rarefaction (expansion)  
regions**

$$P_A = \sqrt{2I\rho c}$$

**P<sub>A</sub> = driving pressure amplitude [Pa]**

**I = irradiation intensity [W m<sup>-2</sup>]**

**(500 W system - 1.3 10<sup>5</sup> W m<sup>-2</sup>)**


**ρ = liquid density [kg m<sup>-3</sup>]**

**c = sound velocity in liquid [m s<sup>-1</sup>]  
(Water 1482 m s<sup>-1</sup>)**

**P<sub>A</sub> = 620 700 Pa = 6.2 bar**

# Ultrasound

Ultrasound frequencies from 20 kHz to 50 MHz



# **Generation of Ultrasound**

**Transducer – a device converting one type of energy into another**

**gas driven**

**whistle (F. Galton), liquid atomizer**

**siren**

**liquid driven**


**liquid whistle homogeniser, a jet of liquid passed through an orifice on a thin metal blade, vibrations, cavitation, mixing of immiscible liquids, ketchup, mayonnaise**

**electromechanical**


**magnetostriuctive, Ni, Co/Fe, Al/Fe, Tb/Dy/Fe alloys shrink when placed in mg. field, solenoid, pulses, upper limit 100 kHz, cooling**

**piezoelectric, oposite charges applied on crystal sides, contraction/expansion, quartz, Pb(Zr/Ti)O<sub>3</sub> ceramics (PZT), up to MHz**


# Generation of Ultrasound



# Sonochemical Reactor



**Piezoelectric Ultrasound Generator  
Ultrasound Processor VCX 500 W**



# Sonochemical Reactor

**Ultrasound Processor VCX 500 W**

Frequency 20 kHz

0 to 40 °C

Argon (flow rate  $62 \text{ cm}^3 \text{ min}^{-1}$ )

TIME of ultrasound treatment

PULSE irradiation and a dwell time 2:2

TEMP maximum temperature 50 °C





AMPL amplitude 50 %




# Sonochemical Reactor

Ti alloy horn, minimum lenght is a half-wavelength of sound in a material, 26 cm for 20 kHz in Ti, multiples of 13 cm

vibration amplitude 5 - 50  $\mu\text{m}$



# Sonochemical Reactor



Sandwich transducer operating at 1-200 kHz

# **Hydrodynamic Cavitation**

**the passage of liquid through an orifice plate**

**the kinetic energy/velocity of the liquid increases at the expense of the pressure**

**throttling causes the pressure to fall (Bernoulli) below the threshold pressure for cavitation (vapor pressure)**

**cavities are generated**


**the liquid jet expands, the pressure recovers**

**energetic collapse of the cavities**


# Hydrodynamic Cavitation

Lord Rayleigh for the British Admiralty 1895

cavitation erosion of propeller blades



$$R \ddot{R} + \frac{3}{2} \dot{R}^2 = \frac{1}{\rho} [p_g - P_0 - P(t)] - 4\nu \frac{\dot{R}}{R} - \frac{2\sigma}{\rho R}$$




The University of Texas at Austin

# Snapping Shrimp

**snaps a claw shut to create a water jet -  
speed of 30 m/s, or 100 km/h**




**a drop of the pressure to below the vapor  
pressure of water - cavitation bubbles  
acoustic pressures of up to 80 kPa at a  
distance of 4 cm**

**The pressure wave is strong enough to kill  
small fish**



M. Versluis, B. Schmitz, A. von der Heydt, D. Lohse, How Snapping Shrimp Snap: Through Cavitating Bubbles. *Science* 289, 2114–2117 (2000)

# Snapping Shrimp



D. Lohse, B. Schmitz, M. Versluis, Nature 413, 477-478 (2001)




# Snapping Shrimp


cavitation bubbles



collapse





intense flash of light



D. Lohse, B. Schmitz, M. Versluis, Nature 413, 477-478 (2001)



# Stable vs. Transient Cavitation



# Acoustic Cavitation

Cavitation effects = creation, growth, and implosive collapse of bubbles ( $1\text{-}2 \mu\text{s}$ )  
in a liquid = implosion HOT SPOT (1 ns)

## TRANSIENT CAVITATION: THE ORIGIN OF SONOCHEMISTRY



stable cavitation - bubbles oscillate for many cycles

transient cavitation - transient cavities expand rapidly collapse violently

# Acoustic Cavitation


**Cavitation effects = creation, growth, and implosive collapse of bubbles in a liquid**

Bubble formation = breakage of liquid during **expansion**, overcoming tensile strength (pure water 1500 bar, only 6.2 bar available)


Weak spots needed = dissolved gas molecules, solid particles, trapped gases

Bubble growth (300 µs), energy absorption, size oscillations

critical size (170-300 µm) = most efficient energy absorption, rapid growth, inefficient energy absorption, collapse



# Acoustic Cavitation



# **Acoustic Cavitation**

**Bubbles collapse = spherically symmetrical implosion,  
shear forces, adiabatic compression, life time 1-2  $\mu$ s**

**Hot spot = end of the collapse  
temperature of the gas inside bubble  
5 000 – 20 000 °C (for 1 ns)**


**surrounding liquid layer 2000 °C**

**pressure 500 – 1500 bar**

**Extreme cooling rates  $10^{10}$  K s<sup>-1</sup>  
red hot steel poured into water 2500 K s<sup>-1</sup>**

# **Homogeneous Sonochemistry**

## **Two-Site Mechanism**




**Cavity interior**  
Filled with gases and vapors

temperatures 5 000 – 20 000 °C  
pressure 500 – 1500 bar

**Surrounding liquid layer**


temperatures 2000 °C

**Bulk liquid**



**Shock waves, shear forces**

# **Homogeneous Sonochemistry Mechanism**



# How to Measure the Temperature inside a Bubble ?

**Sonoluminescence - Light generated during the implosive collapse of bubbles in liquids irradiated with ultrasound**

**95% H<sub>2</sub>SO<sub>4</sub>(aq.)  
under Ar**

**20 kHz (14 W/cm<sup>2</sup>)**


**Ti horn directly immersed**

**T = 298 K**

**Kenneth S. Suslick  
University of Illinois**

- Apparent blackbody temperature
- Ar emission
- SO and O<sub>2</sub><sup>+</sup> emission

**8 000 – 15 000 K**



# Temperature/Pressure inside a Bubble

## Neppiras Equation

$$T_{\max} = T_0 \frac{P_a(\gamma - 1)}{Q} \quad P_{\max} = Q \left( \frac{P_a(\gamma - 1)}{Q} \right)^{\frac{\gamma}{\gamma - 1}}$$

**P<sub>a</sub>** = acoustic pressure


**T<sub>0</sub>** = solution temperature

$\gamma = C_p/C_v$

**Q** = gas pressure inside a bubble  
upon initiation of the collapse,  
at its maximum size

Gas	$\gamma = C_p/C_v$
Kr	<b>1.66</b>
Ar	<b>1.66</b>
He	<b>1.63</b>
O <sub>2</sub>	<b>1.41</b>

# Fate of Bubbles under Ultrasonic Irradiation



**Rectified diffusion – during expansion phase the bubble has larger surface area – more gas diffuses inside than during compression gets out**

# **Single Bubble Sonoluminescence SBSL**

**D. F. Gaitan, L. A. Crum, 1990**


**a method to trap a single  
sonoluminescing bubble within an  
acoustic standing wave field**

**Standing acoustic wave field**

**One bubble trapped**

**The bubble oscillates for many cycles**

**Bubble sonoluminescence**



# Single Bubble Sonoluminescence

## SBSL

D. F. Gaitan, L. A. Crum, 1990

Standing acoustic wave field 1 bar


One bubble levitates in the acoustic field

The bubble oscillates for many cycles

Bubble sonoluminescence


C. A. and V. Bjerknes

The force on an object in a liquid depends on its volume and the pressure gradient, the time averaged force drives the bubble towards the antinode of sound pressure and keeps it there.




# Single Bubble Sonoluminescence SBSL

Proper conditions for a single sonoluminescing bubble within an acoustic standing wave field



# Single Bubble Sonoluminescence SBSL

Sonoluminescence  
Pulses 50 ps




# Single Bubble Sonoluminescence SBSL

Red – MBSL in dodecane

Blue – MBSL in water, 16 kHz


Green – SBSL in water, 43 kHz

Black – blackbody curve for 16200 K





# Single Bubble Sonoluminescence

## SBSL



Red - bubble radius  
Green - bubble temperature  
Blue - acoustic pressure 1.3 bar/25 kHz



# **Multi Bubble Sonoluminescence**

## **MBSL**




**Multi-bubble sonoluminescence**

**Spatial and temporal average**

**250 bar**

# Sonoluminescence

Light generated during the implosive collapse of bubbles in liquids irradiated with ultrasound



Apparent  
blackbody  
temperature  
(all 4 spectra)


**$12500 \pm 1500$  K**

# Sonoluminescence

95% H<sub>2</sub>SO<sub>4</sub>(aq.)

blackbody temperature

Ar emission




an optically  
opaque  
plasma core

# Sonoluminescence

95% H<sub>2</sub>SO<sub>4</sub>(aq.)

SO and O<sub>2</sub><sup>+</sup> emission  
with vibronic progression






$1580 \pm 110$  K at 3.3 bar

$2470 \pm 170$  K at 4.2 bar

$3480 \pm 240$  K at 5.1 bar

# Sonofusion Fraud






# Sonofusion Fraud

Degassed deuterated acetone



$4 \times 10^5 \text{ neutrons s}^{-1}$



# Power Measurement in Sonochemistry

## Calorimetry


**P** = power, **W**

**P<sub>el</sub>** = input power to generator

**P<sub>hf</sub>** = high-freq. power output

**P<sub>th</sub>** = power input into liquid

$$P_{th} = \frac{dT}{dt} c_p m$$



# Power Measurement in Sonochemistry

## Calorimetry

P = power, W

T = temperature, K

t = time, s

c<sub>p</sub> = heat capacity, J g<sup>-1</sup> K<sup>-1</sup>

m = mass, g

Volume 50 cm<sup>3</sup>

Argon atmosphere


Error 5%

heat capacity, J g<sup>-1</sup> K<sup>-1</sup>

Water                  4.2

Tetraglyme        2.08

$$P = \frac{dT}{dt} c_p m$$



# Power Measurement in Sonochemistry

## Chemical dosimetry

The Weissler reaction





Volume 50 cm<sup>3</sup>

KI 0.1 M

CCl<sub>4</sub> 0.2 cm<sup>3</sup>

Time 30 min





I<sub>3</sub><sup>-</sup>

$\lambda_{\max} = 355 \text{ nm}$

$\varepsilon = 26303 \text{ dm}^3 \text{ mol}^{-1} \text{ cm}^{-1}$

# Weissler Reaction



# Power Measurement in Sonochemistry

## Chemical dosimetry

### The Fricke reaction

Volume 50 cm<sup>3</sup>

(NH<sub>4</sub>)<sub>2</sub>Fe(SO<sub>4</sub>)<sub>2</sub>·6H<sub>2</sub>O  
0.001 M

H<sub>2</sub>SO<sub>4</sub> 0.4 M

NaCl 0.001 M

Time 30 min





Fe<sup>3+</sup>

$\lambda_{\max} = 304 \text{ nm}$

$\epsilon = 2197 \text{ dm}^3 \text{ mol}^{-1} \text{ cm}^{-1}$

# Fricke Reaction



# Power Measurement in Sonochemistry

Chemical dosimetry

Porphyrin decomposition ratio

$$1 - R_{TPPS} = 1 - \frac{c_{TPPS}^0}{c_{TPPS}}$$

TPPS


$3.3 \times 10^{-6}$  M

Volume 50 cm<sup>3</sup>


TPPS

$\lambda_{\text{max}} = 412$  nm


$\epsilon = 500000$  dm<sup>3</sup> mol<sup>-1</sup> cm<sup>-1</sup>



# Porphyrin Decomposition





# Power Measurement in Sonochemistry



# Reactor Optimization

cavitating bubbles in the optimised cell (water, 20 kHz,  $P_{us} = 10 \text{ W}$ )  
and simulated intensity distribution for the same geometry



# **Heterogeneous Sonochemistry**

**Solid surfaces = implosion, microjets, shock waves**

**200 µm minimum particle size at 20 kHz for microjets**

**surface erosion**


**removal of unreactive coatings (oxides, nitrides, carbonaceous)**

**fragmentation of brittle materials, increased surface area**




# Heterogeneous Sonochemistry

LARGE PARTICLES



surface cavitation due to defects  
leading to **fragmentation**

SMALL PARTICLES



collision can lead to **surface erosion** or **fusion**


# Heterogeneous Sonochemistry

**Solid particles in liquid = shock waves**

**high speed interparticle collisions (500 km/s)**

**surface smoothing, surface coating removal  
Ni catalytic activity in hydrogenation increased  
 $10^5$  fold by NiO removal**

**localized melting of metal particles at the impact point fragmentation, increased surface area  
intercalation rates enhanced 200 fold in layered oxides and sulfides ( $V_2O_5$ ,  $MoO_3$ ,  $MoS_2$ ,  $ZrS_2$ ,  $TaS_2$ )**









# Heterogeneous Sonochemistry

Metal powders

Cr (mp 2130 K) and Mo (mp 2890 K) agglomerate

W (mp 3683 K) does not

temperature at the point of  
impact  $\sim 3000$  °C



Before ultrasound

30 min. ultrasound

# Cavitational Corrosion of the Tip




# **Control of Sonochemical Reactions**

**sound intensity - minimum for cavitation threshold, depends on frequency, optimum intensity for given reaction conditions, at high powers great number of bubbles hinder sound transmission, decoupling of a liquid from the source, breakdown of transducer material,  $10 - 100 \text{ W cm}^{-2}$**

**sound frequency - 20 – 100 kHz, the higher the frequency, the higher power needed to actuate cavitation, stronger cavitation effects, rarefaction phase shortens at high frequency**

**sound attenuation - proportional to the frequency, more power needed at high frequencies**

# Effect of Frequency on Cavitation in Water



The frequency dependence of the intensity required to produce cavitation for degassed water at room temperature. The intensity required to produce vaporous cavitation above the frequency of 100 kHz rises rapidly.

# **Control of Sonochemical Reactions**

**volatile reactants - primary reaction site inside the bubbles, diameter 200 µm, 5000 °C, easy bubble formation, more reactant vapors inside bubbles, but the cavitation is cushioned**



**nonvolatile reactants - reaction in the thin layer (200 nm) surrounding the bubble, 2000 °C, less cushioning, more energetic cavitation (collapse)**

**high boiling solvents - high vapor pressure inside the bubble cushions the implosion, nonvolatile solvents give less cushioning, more energetic cavitation**

**less cavitation in viscous liquids, viscosity resists shear forces**

**low surface tension facilitates cavitation, in water add surfactants**

# **Control of Sonochemical Reactions**

**temperature - higher temperature increases vapor pressure of a medium, lowers viscosity and surface tension, many bubbles formed at temperatures close to solvent boiling point, a barrier to sound transmission, reaction rates decrease with increasing temperature, more vapors in bubbles**

**ambient gas**

**energy developed on bubble collapse:**


**monoatomic (Ar) > diatomic (N<sub>2</sub>) > triatomic (CO<sub>2</sub>)**

**Xe: low thermal conductivity, heat of the collapsing cavity retained**

**He: high thermal conductivity, heat of the collapsing cavity dissipitated, no reaction**

**external pressure - higher pressure suppresses bubble formation but makes cavitation more energetic, optimum pressure for a given frequency**

# Effect of Temperature on Cavitation in Water



The effect of temperature on cavitation and its associated hysteresis effect for tap water. The increase in intensity as the temperature is increased can be observed before it falls away at the boiling point. When the temperature is allowed to fall an increase in intensity is found in the region of 50-60 °C. This is quite a significant effect and appears to occur in all liquids.

# Sonochemical Reactions

**Solid surfaces = implosion, microjets, shock waves**

**200 µm minimum particle size at 20 kHz for microjets  
surface erosion**

**removal of unreactive coatings (oxides, nitrides, carbonaceous)  
fragmentation of brittle materials, increased surface area**

**Li, Mg, Zn, Al, Cu react at room temperature**



# **Homogeneous Sonochemical Reactions**

**Liquids = heating/cooling by cavity implosions**



**precursor decomposition:**




**nitrides, carbides, sulfides**

**alkane cracking**

**polymer degradation, lower MW, surface modification**

**emulsification of immiscible liquids (oil-water, Hg-organics, polymer-inorganics)**

## **M(acac)<sub>n</sub> as Precursors**




**M(acac)<sub>3</sub>**

- Well studied class of compounds
- Many elements form acac complexes
- Metal complexes – precursors in CVD, sol-gel, thermolysis routes to oxides
- Easily chemically modified
- Volatile, organics soluble
- Nontoxic


# Chemistry of M(acac)<sub>n</sub> Precursors

## Thermal decompositon pathway




Ismail, H. M. *J. Anal. Appl. Pyrolysis* 1991, 21, 315–326.

## Ligand Removal by Water




Pinkas, J.; Huffman, J. C.; Baxter, D. V.; Chisholm, M. H.; Caulton, K. G. *Chem. Mater.* 1995, 7, 1589–1596.

# Sonochemical Synthesis of Iron Oxide Nanoparticles



Cao, X.; Prozorov, R.; Koltypin, Y.; Kataby, G.; Felner, I.; Gedanken, A. *J. Mater. Res.* 1997, 12, 402–406.


Cao, X.; Koltypin, Yu.; Prozorov, R.; Katabya, G.; Gedanken, A. *J. Mater. Chem.* 1997, 7, 2447–2451.



**Amorphous product, by heating to 700 °C converted to  $\alpha\text{-Fe}_2\text{O}_3$  20–40 nm**

Nikitenko, S. I.; Moisy, Ph.; Seliverstov, A. F.; Blanc, P.; Madic, C. *Ultrasonics Sonochem.* 2003, 10, 95–102.


# Sonochemical Synthesis of Iron Oxide Nanoparticles




J. Pinkas, V. Reichlova, R. Zboril, Z. Moravec, P. Bezdicka, J. Matejkova: Sonochemical synthesis of amorphous nanoscopic iron(III) oxide from  $\text{Fe}(\text{acac})_3$

*Ultrasonic Sonochem.* 2008, 15, 256-264


Defect spinel



Corundum



# SEM of Nanoscopic $\text{Fe}_2\text{O}_3$



Particle size 20 - 30 nm

Spherical shape

Uniform size distribution



ISI


SEI

5.0kV X150,000

100nm

WD 3.0mm

# IR Spectrum of Sono- $\text{Fe}_2\text{O}_3$




# IR Spectrum of Sono- $\text{Fe}_2\text{O}_3$

Acetate stretching  
Diketonate vibr. absent

$\nu_{\text{as}}(\text{COO})$   
 $1566 \text{ cm}^{-1}$


$\nu_s(\text{COO})$   
 $1432 \text{ cm}^{-1}$

$$\Delta = \nu_{\text{as}}(\text{COO}) - \nu_s(\text{COO}) = 134 \text{ cm}^{-1}$$



# Decomposition of Acac Ligands

Speculation about the nature of residual organic groups



# Deacon-Phillips Rules


$$\Delta = \nu_{as}(\text{COO}) - \nu_s(\text{COO})$$

$$\Delta \text{CH}_3\text{COO}^- = 164 \text{ cm}^{-1}$$

$\Delta$  larger than ionic form = unidentate



$\Delta$  smaller than ionic form = bidentate

$\Delta$  comparable to ionic form = bridging




Deacon, G. B.; Phillips, R. J. *Coord. Chem. Rev.* 1980, 3, 227–250.



**TEM  
proves amorphous  
character  
of sono- $\text{Fe}_2\text{O}_3$**



# **Crystallization of Amorphous $\text{Fe}_2\text{O}_3$ under TEM Beam**




**Electron diffraction**



**Maghemite or Magnetite**




**Time under TEM beam**




HR-TEM

$\text{Fe}_2\text{O}_3$  calcined at 300 °C

**Crystallization induced  
by heating (300 °C)**




**TEM of amorphous  $\text{Fe}_2\text{O}_3$**



**TEM**

**$\text{Fe}_2\text{O}_3$  calcined at 300 °C**




**Smaller particle size  
on calcination – why?**

# Specific Surface Area



**Surface area** 48 to 260 m<sup>2</sup> g<sup>-1</sup> (BET) depending on H<sub>2</sub>O content

**BET surface area of the Fe<sub>2</sub>O<sub>3</sub> heated to different temperatures during 12h outgassing periods**





The oxide surface area increases as the acetate groups are removed, then the particle size increases because of sintering

# Composite Particles of Sono- $\text{Fe}_2\text{O}_3$



# Composite Particles of $\text{Fe}_2\text{O}_3$



# XRD


of amorphous  $\text{Fe}_2\text{O}_3$

heated dynamically in air


up to 250, 300, and 360 °C

## Maghemite


$\gamma$  -  $\text{Fe}_2\text{O}_3$



# **TEM of $\text{Fe}_2\text{O}_3$ Calcined at 600 °C**




# HT-XRD of Sono- $\text{Fe}_2\text{O}_3$ 280 - 390 °C



Ramp 1 °C min<sup>-1</sup>, 1 min equilb., 30 min data collect., 10 °C steps

# Hematite Particle Size



**Dependence of the coherence length, D (nm) of  $\alpha$ - $\text{Fe}_2\text{O}_3$  on the crystallization temperature under dynamic-isothermal conditions of the HT-XRD measurement**