

A Unified Synthetic Approach to Porous Hybrid Single-Site Metallosilicates

Martin Kejík,¹ Zdeněk Moravec,¹ Lucie Šimoníková,¹ Aleš Stýskalík,¹ Craig E. Barnes,² Jiří Pinkas¹

¹Masaryk University, Department of Chemistry, CZ-61137 Brno, Czech Republic, 380095@mail.muni.cz

² University of Tennessee, Department of Chemistry, Knoxville, TN 37996-1600, USA

A generalized low-temperature non-hydrolytic sol-gel strategy to produce uniformly dispersed metallosilicate sites in highly porous hybrid silicate matrices is reported. The readily available spherosilicate molecular building block $(\text{Me}_3\text{Sn})_8\text{Si}_8\text{O}_{20}$ is cross-linked in two steps by irreversible condensation reactions with high-valence d- and p-block chlorides and alkyl-metals in toluene or THF to form statistically connected rigid amorphous networks. Initially, a limited amount of the metal site precursor (e.g., TiCl_4 , VOCl_3 , Py-AlCl_3 , $\text{Et}_3\text{N-AlMe}_3$, $[\text{Me}_4\text{N}^+][\text{AlCl}_4^-]$, ZnEt_2 , SbCl_3 , Ph_3SbCl_2 , ...) is introduced to an excess of the building block to achieve full condensation and uniformity. A minimum site separation of ≈ 1 nm is ensured by the bulky building block. In the second step, a limited amount of a ditopic hybrid linker ($\text{ClMe}_2\text{SiCH}_2\text{CH}_2\text{SiMe}_2\text{Cl}$ or $\text{ClMe}_2\text{Si}(\text{C}_6\text{H}_4)(\text{C}_6\text{H}_4)\text{SiMe}_2\text{Cl}$) is added to produce extensively cross-linked gels while maximizing the probability of full condensation. The byproducts of the condensations (Me_3SnCl or Me_3SnR) are inert and volatile and they do not interfere with subsequent steps. Removal of all volatiles under vacuum affords pure materials, while the mass of the lost byproducts can be used to monitor condensation by gravimetric techniques with great precision. Since a kinetically-driven approach and mild conditions are used, it is possible to produce a variety of complex sites incorporating organic ligands and sensitive moieties ($\text{Py-Al}(\text{OSi}\equiv)_3$, $\text{Sb}(\text{OSi}\equiv)_3$, $\text{Ph}_3\text{Sb}(\text{OSi}\equiv)_2$). The prepared xerogels were characterized by IR and MAS NMR spectroscopies, gas adsorption, gravimetry, STEM/EDS, ICP-OES, and TG/DSC. The fundamental limits of the system and the interplay of parameters, such as site loading, linker flexibility, stoichiometry, and solvent effects, were explored and correlated with structure, condensation, and porosity. A method of molecular texture elucidation using the linker as a two-point correlation probe was developed. Additionally, a series of quantum mechanical DFT calculations were conducted to help explain observed behaviors and to make predictions for the stability and reactivity of additional, as-of-now untested, precursors as well as creating a baseline for future calculations.

The financial support by GAČR Junior 20-03636Y is gratefully acknowledged. CIISB research infrastructure project LM2018127 funded by MEYS CR is gratefully acknowledged for the financial support of the measurements at the Josef Dadok National NMR Centre.